

NRL Report 6213

High Temperature Properties of Sodium, Potassium, and Cesium

Thirteenth Progress Report

J. P. STONE, C. T. EWING, J. R. SPANN, AND R. R. MILLER

*Inorganic and Nuclear Chemistry Branch
Chemistry Division*

January 15, 1965

FACILITY FORM 602

N65-30487

(ACCESSION NUMBER)

(PAGES)

CF-64221
(NASA CR OR TMX OR AD NUMBER)

(THRU)

(CODE)

(CATEGORY)

GPO PRICE \$ _____

CFSTI PRICE(S) \$ _____

Hard copy (HC) _____

Microfiche (MF) _____

ff 653 July 65



U.S. NAVAL RESEARCH LABORATORY
Washington, D.C.

2/30212

High Temperature Properties of Sodium, Potassium, and Cesium

Thirteenth Progress Report

J. P. STONE, C. T. EWING, J. R. SPANN, AND R. R. MILLER

*Inorganic and Nuclear Chemistry Branch
Chemistry Division*

An experimental program to measure various thermo-physical properties of sodium, potassium, cesium, and their vapors at elevated temperatures has been completed at NRL. Preliminary data for the density of liquid potassium (1099° to 2287°F) and the vapor pressure of cesium (1214° to 2345°F) are presented in this report.

36 467

26.16

INTRODUCTION

In the development of compact turboelectric systems, the National Aeronautics and Space Administration is sponsoring a property measurement program for the evaluation of several liquid metals as possible working fluids. As an integral part of this program, the Naval Research Laboratory is engaged in the measurement of various thermo-physical properties of sodium to 2500°F, potassium to 2300°F, and cesium to 2300°F.

SUMMARY OF EXPERIMENTAL PROGRAM

For the three alkali metals, the properties which are being determined experimentally include vapor pressure, specific volume of liquid, specific heat of liquid (except for cesium), surface tension of liquid (except for sodium), and specific volume of saturated and superheated vapors (PVT studies). Additional thermodynamic properties including latent heat of vaporization, enthalpy, entropy, and specific heat of the vapor will be calculated from the measured properties.

The experimental phases of the PVT studies for both sodium and potassium have been completed. The thermodynamic properties of potassium including specific volume, enthalpy, entropy,

and specific heat were obtained from a comprehensive thermodynamic treatment of the vapor and liquid properties. A preliminary reporting of this treatment and tables of the thermodynamic properties were included in the Twelfth Progress Report (1). A treatment of the sodium data similar to that described for potassium (1) is in progress, and tabular properties should be available for inclusion in the next quarterly report. PVT measurements for cesium are in progress, and preliminary saturation pressures are reported.

Densities of liquid potassium from 1099° to 2287°F have been completed, and final values are reported. Densities of sodium for the temperature range from 2100° to 2500°F were reported in the Sixth Progress Report (2). Additional sodium measurements at lower temperatures and the cesium measurements are in progress.

The surface tension measurements of liquid potassium and cesium have been delayed by the PVT work and by problems experienced in the welding of the maximum-bubble-pressure apparatus. However, measurements are expected to be made during the last quarter of this fiscal year.

DENSITY OF LIQUID POTASSIUM

The final density measurements of potassium are reported in Table 1. Pycnometers of Cb-1%Zr with 30 cc nominal volumes are used for the determinations. The method employed is as follows. The alkali metal is distilled into the pycnometer, and an overflow vessel is welded to the

NRL Problem C05-15; NASA Contract NAS C-76320. This is an interim report for the period 1 October to 31 December 1963. While this report numerically precedes the 14th progress report, it has been written afterwards to complete this series. The experimental work was terminated on 1 October 1964. Three technical reports will follow, one each on potassium, sodium, and cesium. Manuscript submitted Nov. 3, 1964.

TABLE 1
Density of Liquid Potassium

Temperature (°F)	Density (lb/cu ft)
1099.0	43.973
1562.6	40.066
1747.0	38.423
1928.0	36.783
2121.7	35.047
2286.7	33.713

top with an interconnecting capillary (3). The apparatus is pressurized (1 atm overpressure at all temperatures), heated to the desired equilibrium temperature, and the weight of metal remaining in the known volume determined both by weight difference and by chemical analysis. The maximum difference of these two weight determinations in all cases has been less than 0.1%.

The recommended density equation for liquid potassium is

$$d = 52.759 - 7.4392 \times 10^{-3}t - 0.5784 \times 10^{-6}t^2 + 0.0780 \times 10^{-9}t^3 \quad (1)$$

where d is density in lb/cu ft and t is temperature in °F. Equation (1), for the temperature range

from the melting point to 2300°F, was derived by fitting the best curve to the density determinations of Hagen (4) and NRL (5) at lower temperatures; Novikov (6), MSA (7), and Rinck (8) at moderate temperatures; and NRL (Table 1) at higher temperatures. For each literature investigation, the average deviation of the observed densities from those calculated using Eq. (1) is presented in Table 2. It will be noted that overlapping density determinations have been made from the melting point to 2300°F and that the bulk of these determinations are represented by Eq. (1) with deviations of less than 0.2%. This indicates a confidence limit for Eq. (1) of ± 0.2 to $\pm 0.3\%$.

SATURATED VAPOR PRESSURE OF CESIUM

Saturation pressures were obtained for cesium from 0.88 atm at 1214°F to 33.5 atm at 2345°F with the null-point apparatus. The data for the full temperature range from the normal boiling point to 2345°F were effectively fitted with one three-term equation.

$$\log p = 5.87303 - \frac{7040.69}{T} - .53290 \log T \quad (2)$$

where p is vapor pressure in abs atm and T is temperature in °R. The average deviation of the observed vapor pressure data from corresponding values computed using Eq. 2 is $\pm 0.35\%$.

TABLE 2
Fit of General Density Equation for
Potassium to Literature Data

Investigator	Temp Range (°F)	Average Deviation of All Observed Values of Each Investigator from Corresponding Values Calculated with Eq. (1) (%)
Hagen	(mp to 229.6)	-0.17
NRL	(mp to 499.1)	± 0.05
Novikov	(196 to 1352)	± 0.20
MSA	(257 to 1281)	+0.81
Rinck	(617 to 1104)	$\pm 0.46^*$
NRL	(1099 to 2287)	± 0.11

*Except for two results, the data of Rinck show an average deviation of $\pm 0.21\%$.

REFERENCES

1. Ewing, C.T., Stone, J.P., Spann, J.R., Steinkuller, E.W., Williams, D.D., and Miller, R.R., "High Temperature Properties of Sodium and Potassium - Twelfth Progress Report for Period 1 July to 30 September 1963," NRL Report 6094, June 9, 1964
2. Stone, J.P., Ewing, C.T., Spann, J.R., Steinkuller, E.W., Kovacina, T.A., and Miller, R.R., "High Temperature Properties of Sodium - Sixth Progress Report for Period 1 January to 31 March 1962," NRL Memo. Report 1312, Apr. 1962
3. Ewing, C.T., Stone, J.P., Spann, J.R., Kovacina, T.A., and Miller, R.R., "High Temperature Properties of Sodium - Fourth Progress Report for Period 1 April to 30 Sept 1961," NRL Memo Report 1236, Oct. 1961
4. Hagen, E.B., *Ann. Physik.* **255**:437 (1883)
5. Ewing, C.T., Atkinson, H.B., Jr., and Rice, T.K., NRL Report C-3287, May 1948
6. Novikov, I.I., Soloviev, A.N., Khabakhpasheva, E.M., Gruzdev, V.A., Pridantsev, A.I., and Vasinina, M.Y., *Atomnaya Energiya*, **1** (No. 4):92 (1956)
7. Jackson, C.B., Wiczorek, G.A., and Van Andel, A., "Density of the System K-Na," Appendix C in "Quarterly Progress Report on the Measurement of the Physical and Chemical Properties of the Sodium-Potassium Alloy, No. 1," by Ewing, C., and Miller, R.R., NRL Report P-3010, Sept. 30, 1946
8. Rinck, E., *Compt. rend.* **189**:39 (1929)

14. KEY WORDS	LINK A		LINK B		LINK C	
	ROLE	WT	ROLE	WT	ROLE	WT
Sodium Potassium Cesium High Temperature Properties Thermodynamic properties						

INSTRUCTIONS

1. **ORIGINATING ACTIVITY:** Enter the name and address of the contractor, subcontractor, grantee, Department of Defense activity or other organization (*corporate author*) issuing the report.

2a. **REPORT SECURITY CLASSIFICATION:** Enter the overall security classification of the report. Indicate whether "Restricted Data" is included. Marking is to be in accordance with appropriate security regulations.

2b. **GROUP:** Automatic downgrading is specified in DoD Directive 5200.10 and Armed Forces Industrial Manual. Enter the group number. Also, when applicable, show that optional markings have been used for Group 3 and Group 4 as authorized.

3. **REPORT TITLE:** Enter the complete report title in all capital letters. Titles in all cases should be unclassified. If a meaningful title cannot be selected without classification, show title classification in all capitals in parenthesis immediately following the title.

4. **DESCRIPTIVE NOTES:** If appropriate, enter the type of report, e.g., interim, progress, summary, annual, or final. Give the inclusive dates when a specific reporting period is covered.

5. **AUTHOR(S):** Enter the name(s) of author(s) as shown on or in the report. Enter last name, first name, middle initial. If military, show rank and branch of service. The name of the principal author is an absolute minimum requirement.

6. **REPORT DATE:** Enter the date of the report as day, month, year, or month, year. If more than one date appears on the report, use date of publication.

7a. **TOTAL NUMBER OF PAGES:** The total page count should follow normal pagination procedures, i.e., enter the number of pages containing information.

7b. **NUMBER OF REFERENCES:** Enter the total number of references cited in the report.

8a. **CONTRACT OR GRANT NUMBER:** If appropriate, enter the applicable number of the contract or grant under which the report was written.

8b, 8c, & 8d. **PROJECT NUMBER:** Enter the appropriate military department identification, such as project number, subproject number, system numbers, task number, etc.

9a. **ORIGINATOR'S REPORT NUMBER(S):** Enter the official report number by which the document will be identified and controlled by the originating activity. This number must be unique to this report.

9b. **OTHER REPORT NUMBER(S):** If the report has been assigned any other report numbers (*either by the originator or by the sponsor*), also enter this number(s).

10. **AVAILABILITY/LIMITATION NOTICES:** Enter any limitations on further dissemination of the report, other than those

imposed by security classification, using standard statements such as:

- (1) "Qualified requesters may obtain copies of this report from DDC."
- (2) "Foreign announcement and dissemination of this report by DDC is not authorized."
- (3) "U. S. Government agencies may obtain copies of this report directly from DDC. Other qualified DDC users shall request through _____."
- (4) "U. S. military agencies may obtain copies of this report directly from DDC. Other qualified users shall request through _____."
- (5) "All distribution of this report is controlled. Qualified DDC users shall request through _____."

If the report has been furnished to the Office of Technical Services, Department of Commerce, for sale to the public, indicate this fact and enter the price, if known.

11. **SUPPLEMENTARY NOTES:** Use for additional explanatory notes.

12. **SPONSORING MILITARY ACTIVITY:** Enter the name of the departmental project office or laboratory sponsoring (*paying for*) the research and development. Include address.

13. **ABSTRACT:** Enter an abstract giving a brief and factual summary of the document indicative of the report, even though it may also appear elsewhere in the body of the technical report. If additional space is required, a continuation sheet shall be attached.

It is highly desirable that the abstract of classified reports be unclassified. Each paragraph of the abstract shall end with an indication of the military security classification of the information in the paragraph, represented as (TS), (S), (C), or (U).

There is no limitation on the length of the abstract. However, the suggested length is from 150 to 225 words.

14. **KEY WORDS:** Key words are technically meaningful terms or short phrases that characterize a report and may be used as index entries for cataloging the report. Key words must be selected so that no security classification is required. Identifiers, such as equipment model designation, trade name, military project code name, geographic location, may be used as key words but will be followed by an indication of technical context. The assignment of links, roles, and weights is optional.

DOCUMENT CONTROL DATA - R&D

(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)

1. ORIGINATING ACTIVITY (Corporate author) U.S. Naval Research Laboratory Washington, D.C. 20390		2a. REPORT SECURITY CLASSIFICATION UNCLASSIFIED	
		2b. GROUP	
3. REPORT TITLE "High Temperature Properties of Sodium, Potassium, and Cesium—Thirteenth Progress Report"			
4. DESCRIPTIVE NOTES (Type of report and inclusive dates) An interim report on one phase of the problem			
5. AUTHOR(S) (Last name, first name, initial) Stone, J.P., Ewing, C.T., Spann, J.R., and Miller, R.R.			
6. REPORT DATE January 15, 1965		7a. TOTAL NO. OF PAGES 5	7b. NO. OF REFS 8
8a. CONTRACT OR GRANT NO. NRL Problem C05-15 b. PROJECT NO. NASA Contr. NAS C-76320 c. d.		9a. ORIGINATOR'S REPORT NUMBER(S) NRL Report 6213 9b. OTHER REPORT NO(S) (Any other numbers that may be assigned this report)	
10. AVAILABILITY/LIMITATION NOTICES Unlimited availability			
11. SUPPLEMENTARY NOTES		12. SPONSORING MILITARY ACTIVITY NASA	
13. ABSTRACT An experimental program to measure various thermo-physical properties of sodium, potassium, cesium, and their vapors at elevated temperatures has been completed at NRL. Preliminary data for the density of liquid potassium (1099° to 2287°F) and the vapor pressure of cesium (1214° to 2345°F) are presented in this report.			